



STOPS RUST® OUTDOOR METALLIC SPRAYS

DESCRIPTION AND USES

Rust-Oleum® Stops Rust® Outdoor Metallic Sprays are designed to provide a durable protective coating with excellent resistance to rust, and excellent resistance to abrasion, fading, chipping, and dulling which will not rub off. These sprays apply easily, provide excellent coverage and dry fast to a tough attractive finish. Rust-Oleum Stops Rust Outdoor Metallic Sprays are ideal for ferrous, non-ferrous metal and wood surfaces. It features a comfort tip with a wider finger pad to reduce fatigue caused by continuous spraying and an any-angle tip which allow s you to spray at any angle. Not for use on galvanized metal.

PRODUCTS

SKU	DESCRIPTION (Aerosol)
7250830	Black Night
7251830	Cobalt Blue
7252830	Racing Green
7256830	Apple Red
7270830	Gold Rush
7271830	Silver Metallic
7272830	Dark Bronze
7273830	Copper
7274830	Antique Brass
7275830	Burnished Brass
7277830	Matte Nickel
224228	Charcoal
244226	Rich Caramel
248636	Oil Rubbed Bronze
248637	Vintage Copper
286524	Warm Gold
286525	Dark Copper
286564	Rose Gold

PRODUCT APPLICATION

Use outdoors or in a well-ventilated area such as an open garage. Use when temperature is between 50°-90°F (10°-32°C) and humidity is below 70% to ensure proper drying. Do not apply to surfaces that, when heated, exceed 200°F (93°C) or galvanized metal. Avoid spraying in very windy, dusty conditions. Cover surrounding area to protect from spray mist.

SURFACE PREPARATION

Remove all dirt, grease, oil, salt and chemical contaminants by washing the surface with a commercial detergent, or other suitable cleaning method. Rinse with fresh water and allow to thoroughly dry. Remove loose paint and rust with a wire brush or sandpaper. Previously coated surfaces must be sound and in good condition. Smooth, hard, or glossy finishes should be scarified by sanding to create a surface profile.

PRODUCT APPLICATION (cont.)

SURFACE PREPARATION (cont.)

WARNING! If you scrape, sand or remove old paint from any surface, you may release lead paint dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE; ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

PRIMING

Use of a Stops Rust® Primer provides added corrosion protection, superior adhesion and hiding and is especially recommended for bare wood and metal. The following primers are recommended.

7769	Rusty Metal Primer
7780	Clean Metal Primer
2081	Light Gray Auto Primer
2067	Red Auto Primer
2089	Dark Gray Auto Primer

APPLICATION

Shake can vigorously for one minute after the mixing ball begins to rattle. If mixing ball fails to rattle DO NOT STRIKE CAN. Contact Rust-Oleum. Shake often during use. Hold can upright 10-16" from surface and spray in a steady back-and-forth motion, slightly overlapping each stroke. Keep the can the same distance from the surface. Keep the can in motion while spraying. Apply two or more light coats a few minutes apart to avoid drips and runs. Do not use near open flame.

DRY & RECOAT

Dry and recoat times are based on 70°F and 50% relative humidity. Allow more time at cooler temperatures. Dries to the touch in 10 minutes, to handle in 30 minutes and is fully dry in 24 hours.

CLEAN-UP

Wipe off tip before storing. Clean-up wet paint with xylene or mineral spirits. Properly discard empty container. Do not burn or place in home trash compactor.

CLOGGING

If the valve clogs, twist and pull off spray tip and rinse in a solvent such as mineral spirits. Do not insert any object into can valve opening.

	TECHNICAL DATA	SRT-07
<small>• TRUSTED QUALITY SINCE 1921 •</small> RUST-OLEUM® 	STOPS RUST® OUTDOOR METALLIC SPRAYS	

PHYSICAL PROPERTIES

		OUTDOOR METALLIC SPRAYS
Resin Type		Solvent Acrylic
Pigment Type		Varies with color
MIR		1.25 Max
Fill Weight		11 ounces
Solvents		Acetone, Toluene, Xylene
Recommended Dry Film Thickness (DFT) Per Coat		1.0-2.0 mils (25-50μ)
Practical Coverage at Recommended DFT (assumes 15% material loss)		4-6 sq.ft./can (0.37-0.56 m ² /can)
Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity	Touch	10 minutes
	Handle	30 minutes
	Fully Dry	24 hours
Dry Heat Resistance		200°F (93°C)
Shelf Life		5 years
Flash Point		156°F (69°C)
Safety Information		For additional information, see SDS

Calculated values are shown and may vary from the actual manufactured material.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.